

CD 26

Repair mortar for concrete, coarse-grained from 30 to 100 mm

Cement mortar for thick layers

CHARACTERISTICS

- ▶ low shrinkage
- ▶ inside and outside use
- ▶ waterproof
- ▶ resistant to frost and de-icing road chemicals
- ▶ fast hardening
- ▶ reinforced with fibres
- ▶ hydrophobic
- ▶ mineral
- ▶ modified with polymers
- ▶ one component
- ▶ very good working parameters
- ▶ for manual and mechanical application

SCOPE OF USE

Ceresit CD 26 is a coarse-grained one component filler to smooth out concrete and reinforced concrete, to fill cracks/voids and repair damaged substrate. The range of application is from 30 to 100 mm. The thickness of the applied mortar can be up to 35 mm in the single application. Ceresit CD 26 may be applied both on vertical and horizontal surfaces inside and outside the buildings. The mortar can be applied on the concrete of the class above C12/15.

Ceresit CD 26 is a part of concrete repair system Ceresit PCC. Ceresit PCC system is designed for filling cracks/voids, re-profiling balconies as well as for making the complex repairs for various types of cement and reinforced concrete structures. It allows repairing the structures, even when they have been severely damaged due to exploitation or destruction under the influence of mechanical or corrosive factors. It is suitable for repairing the following types of constructions: balconies, overpasses, reinforced concrete ditches, ceilings, etc. It may be also used for repairing such construction objects as concrete and reinforced concrete tanks (including waste treatment plants), flyovers, frame structures and multi board structures, monolithic structures (including swimming pools), reinforced concrete, chimneys, refrigerators, etc. Products of Ceresit PCC system are resistant to weather conditions and direct impact of de-icing road chemicals, including salts. They are characterised with water resistance and diffusion, as well as extensive carbonised resistance due to which they contribute to the extension of the construction lifetime. Do not use for repairing light concrete.



SUBSTRATE PREPARATION

Ceresit CD 26 adheres to crack-free, load-bearing, clean concrete substrates free from any substances, which may impair adhesion. The substrate should have sufficient compressive strength (concrete class above C12/15) and pull-off strength of minimum 1,0 MPa.

Concrete

Corroded and carbonated concrete and any loose elements should be carefully removed. Any stains, the layer of cement wash, anti-adhesion agents, old layers should be mechanically removed. The surface of the concrete should be rough and porous, ensuring good adhesion. The substrate should be mechanically prepared e. g. through abrasive blasting, grounding or milling.

Reinforcement

The corroded reinforcing bars should have the concrete support removed up to the places which are not corroded. The reinforcing bars should have rust removed by sand – blasting to the degree of cleanliness of Sa 2,5 so that they acquire clear, metallic appearance and then they should be cleaned with compressed, oil free air. Before the application of Ceresit CD 26, the uncovered reinforced bars should be covered with anti-corrosion protection CD 30 twice. Concrete substrates should be sprayed with water without any puddles formed and then the slightly damp substrates and the previously protected reinforced steel

should be covered with the contact layer Ceresit CD 30. The repair mortar should be applied on the slightly damp contact layer, however, not longer than after 30–60 minutes. In case of exceeding this time, the contact layer should be applied once again provided that the previous layer is completely dry.

APPLICATION

Preparation of the mortar:

The content of the packaging should be poured to the measured amount of clean water and mixed with the slow rotating drill with a mixer until the homogenous mass without lumps is obtained. Then it is necessary to wait 3 minutes and mix the mortar once again.

Application of the mortar:

Within the pot life the ready mortar should be applied with the trowel on the freshly applied contact layer or poured to the form and it should be properly structured. In case of larger areas it is advisable to use vibration scantlings. The surface of the filler should be smoothed with the steel trowel or with the plastic trowel or sponge within approximately 10–20 minutes. Mortar Ceresit CD 26 may be applied with the application of a gunite method. Mortar CD 26 can be applied on the single application on the vertical surfaces up to 35 mm thickness. In case of the application of mortar in a few layers or the application on mortar CD 25 on CD 26 the time between the consecutive applications should not exceed 3 hours. Otherwise it is necessary to wait 24 hours, to make the substrate damp with water, to apply contact layer and then the repair filler should be applied. Mortar Ceresit CD 26 can be used as the final layer. After 2 days mortar Ceresit CD 26 can be covered with the filler Ceresit CD 24.

Additional protection of concrete:

The additional protection for concrete against corrosion, harmful water impact, frost, aggressive agents and weather is to cover the mortar of CD 26 with acrylic paint Ceresit CT 44 or flexible insulation layer Ceresit CR 166. These layers can be applied after 3 days when CD 26 has been applied.

PLEASE NOTE

Use CD 26 only in dry conditions, the temperatures from +5 to +30 °C and relative humidity below 80 %.

The mortar should be protected against too fast drying caused by the strong insolation, draughts, etc. The mortar should be protected against rain until it dries completely. Then it is recommended to use the scaffolding protection. All data refer to the temperature +20 °C and air relative humidity 60 %. Faster or slower material hardening may occur in different conditions. Fresh stains should be washed with water, whereas the hardened ones should be removed only in a mechanical manner. The mortars should not be mixed with other additives and it should not be covered with materials containing gypsum. CD 26 contains cement and when mixed with water it causes alkaline reaction. Therefore skin and eyes should be protected. In case of contact with eyes they should be rinsed with water and the general practitioner should be consulted. Chromium VI content– below 2 ppm during the lifetime of the product.

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards of the German Standards Institute (DIN). The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23 °C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

Henkel Polska Sp. z o.o.
 Domaniewska 41, PL-02-672 Warsaw
 Phone + 48 22 56 56 300, Fax + 48 22 56 56 309
 Internet: www.ceresit.henkel.com · E-Mail: ceresit.bautechnik@henkel.com

TECHNICAL DATA

Base:	cement with mineral fillers and high quality powder resin
Colour:	grey
Grain size:	0÷5 mm
Mixing ratio:	approximately 3–3,2 l water per 25 kg
Maturing time:	approximately 3 min.
Pot life:	approximately 30 min.
Application temp.:	from +5 to +30 °C
Next layer application:	– time between the application of subsequent layers of mortar CD 26: max. until 3 hours – application of the filler: after approximately 2 days – application of protective layers: after approximately 3 days
Shrinkage after 28 days:	≤ 0,08 %
Resilience module with compression:	≥ 18 GPa
Compressive strength after 28 days:	≥ 40 MPa
Bending tensile strength after 28 days:	≥ 9,0 MPa
Adhesive tension strength with contact layer, after 28 days:	≥ 1,5 MPa
Temperature resistance:	from –50 to +70 °C
Rain resistance:	after approximately 24 hours
Consumption:	approximately 2 kg/m ² /1 mm thickness
Storage:	Up to 12 months since the production date when stored on pallets in dry conditions and in original undamaged packages.

This product possesses the technical approval No AT-15-7290/2007 issued by Instytut Techniki Budowlanej and National Declaration of Conformity No CD 25/1/07 dated on 23.04.2007.

Should you need support or advice, please consult our advisory service for architects and craftsmen on the hotline numbers

Phone: +49 211 797 0

Fax: +49 211 798 2148

Ceresit



BAUTECHNIK